

Amendments to the Claims:

10/525195
DT01 Rec'd PCT/PT 18 FEB 2005

The following listing of claims will replace all prior versions, and listings, of claims in the application:

1. (Currently Amended) A penetration-resistant material comprising at least a double layer of woven ~~woven~~-fabric wherein the double layer comprises a first layer of fabric composed of a first set of threads comprising 3.5 to 20 threads/cm, having a linear density of at least 210 dtex, and comprising at least 65 % of the first layer fabric weight, and a second set of threads comprising 0.5 to 16 threads/cm and having a linear density of at least 50 dtex, with the second set of threads being transverse to the first set of threads, and ~~a~~ the ratio of the number of threads/cm of the first set to that of the second set is > 1 , and a second layer of fabric composed of a first set of threads comprising 0.5 to 16 threads/cm and having a linear density of at least 50 dtex, and a second set of threads comprising 3.5 to 20 threads/cm, having a linear density of at least 210 dtex, and comprising at least 65 % of the second layer fabric weight, with the second set of threads being transverse to the first set of threads, and ~~a~~ the ratio of the number of threads/cm of the second set to that of the first set is > 1 , and wherein the first and second sets of threads of the first layer have a parallel orientation towards the first and second sets, respectively, of threads of the second layer, wherein ~~characterized in that~~ in the first layer of fabric at least the first set of threads, and in the second layer of fabric at least the second set of threads, are treated with a water-repellant.
2. (Currently Amended) The penetration-resistant material of claim 1, wherein in the first layer of fabric the first and the second set of threads, and in the second layer of fabric the first and the second set of threads, are treated with a water-repellant.
3. (Currently Amended) The penetration-resistant material of claim 1 ~~or 2~~ wherein the water-repellant comprises fluorine ~~fluor~~ and carbon atoms.

4. (Currently Amended) The penetration-resistant material of claim 3, wherein the water-repellant comprises a mixture of fluoroacrylate ~~fluoroacrylate~~ polymers.

5. (Currently Amended) The penetration-resistant material of claim 1, ~~any one of claims 1 to 4~~ wherein the water-repellant treated threads comprise about 0.1 to about 2 weight % fluoroacrylate ~~fluoroacrylate~~ polymers with respect to the weight of the water-repellant treated threads.

6. (Currently Amended) The penetration-resistant material of claim 1, ~~any one of claims 1 to 5~~ wherein at least the ratio of the linear density of the first set of threads to the linear density of the second set of threads of the first layer and of the linear density of the second set of threads to the linear density of the first set of threads of the second layer is > 1 .

7. (Currently Amended) The penetration-resistant material of claim 6, wherein at least the ratio of the linear density of the first set of threads to the linear density of the second set of threads of the first layer and of the linear density of the second set of threads to the linear density of the first set of threads of the second layer is > 4.2 .

8. (Currently Amended) The penetration-resistant material of claim 6, ~~or 7~~ wherein at least the ratio of the linear density of the first set of threads to the linear density of the second set of threads of the first layer and of the linear density of the second set of threads to the linear density of the first set of threads of the second layer is > 5.9 .

9. (Currently Amended) The penetration-resistant material of claim 1, ~~any one of claims 1 to 8~~ wherein at least one of the second set of threads of the first layer and the first set of threads of the second layer comprises 0.5 to 8 threads/cm.

10. (Currently Amended) The penetration-resistant material of claim 1, ~~any one of claims 1 to 9~~ wherein the threads of the layers of the double layer are bonded together.

11. (Currently Amended) The penetration-resistant material of claim 10, wherein the threads of the layers of the double layer are bonded together with an adhesive material.

12. (Currently Amended) The penetration-resistant material of claim 1, ~~any one of claims 1 to 11~~ wherein the first set of threads of the first layer and the second set of threads of the second layer consist of high tenacity threads selected from aramid, polyethylene and poly-p-phenylenebenzobisoxazole (PBO) threads.

13. (Currently Amended) The penetration-resistant material of claim 1, ~~any one of claims 1 to 12~~ wherein the second set of threads of the first layer and the first set of threads of the second layer are selected from polyester, polyethylene, polypropylene and aramid threads.

14. (Currently Amended) The penetration-resistant material of claim 1, ~~any one of claims 1 to 13~~ wherein the first set of threads of the first layer and the second set of threads of the second layer consist of aramid threads, and the second set of threads of the first layer and the first set of threads of the second layer consist of polyester threads.

15. (Currently Amended) The penetration-resistant material of claim 1, ~~any one of claims 1 to 14~~ wherein the linear density of the first set of threads of the first layer and of the second set of threads of the second layer is 210 to 6720 dtex.

16. (Currently Amended) The penetration-resistant material of claim 15, wherein the linear density of the first set of threads of the first layer and of the second set of threads of the second layer is 420 to 3360 dtex.

17. (Currently Amended) The penetration-resistant material of claim 15, ~~claims 15 or 16~~ wherein the linear density of the first set of threads of the first layer and of the second set of threads of the second layer is 420 to 1680 dtex.

18. (Currently Amended) The penetration-resistant material of claim 15, ~~claims 15, 16 or 17~~ wherein the linear density of the first set of threads of the first layer and of the second set of threads of the second layer is 840 to 1100 dtex.

19. (Currently Amended) The penetration-resistant material of claim 1, ~~any one of claims 1 to 18~~ wherein the linear density of the second set of threads of the first layer and of the first set of threads of the second layer is 50 to 280 dtex.

20. (Currently Amended) The penetration-resistant material of claim 19, wherein the linear density of the second set of threads of the first layer and of the first set of threads of the second layer is 80 to 140 dtex.

21. (Currently Amended) The penetration-resistant material of claim 1, ~~any one of claims 1 to 20~~ wherein the first set of threads of the first layer and the first set of threads of the second layer are warp threads and the second set of threads of the first layer and the second set of threads of the second layer are weft threads.

22. (Currently Amended) The penetration-resistant material of claim 1, ~~any one of claims 1 to 21~~ wherein the double layer exhibits ~~exhibits~~ two outer sides and at least one of the outer sides of the double layer is provided with a protective layer.

23. (Currently Amended) An article comprised ~~made~~ of the penetration-resistant material of ~~any one of claims 1 to 22~~ claim 1.